OCT-09-2006 15:26

Docket No. - BAT 0033 NA/40078.251/12755CON1

Amendments to the Claims

9374496405

The following listing of claims will replace all prior versions, and listings, of claims in the present application:

- 1. (Previously Presented) A cellulosic fiber composite comprising:
 - a cellulosic material; and
 - a resin binder comprising vegetable protein hydrolysates and a synthetic resin, wherein the synthetic resin is phenolic resin, isocyanate resin, or combinations thereof, and

the resin binder is present in an amount of less than 40% by weight of the composite.

- 2. (Original) The composite as claimed in claim 1 further comprising an average moisture content between about 8% and about 35% by weight.
- The composite as claimed in claim 1 wherein the vegetable protein is soy protein. 3. (Original)
- The composite as claimed in claim 3 wherein the soy protein is soy isolate. 4. (Original)
- 5. (Original) The composite as claimed in claim 3 wherein the soy protein is soy flour.
- 6. (Original) The composite as claimed in claim 3 wherein the soy protein is a blend of soy isolate and soy flour.
- 7. (Original) The composite as claimed in claim 6 wherein the weight ratio of the blend of soy isolate to soy flour is about 50:50.
- 8. (Original) The composite as claimed in claim 1 wherein the synthetic resin is phenolic resin.
- 9. (Original) The composite as claimed in claim 8 wherein the phenolic resin is phenol

Serial No. 10/698,217

Docket No. - BAT 0033 NA/40078.251/12755CON1

formaldehyde.

- 10. (Currently Amended) The composite as claimed in claim 8 wherein the resin binder has a weight ratio of protein hydrolysates to phenolic resin between about 10:90 and about 90:10.
- 11. (Original) The composite as claimed in claim 8 wherein the resin binder has a weight ratio of protein hydrolysates to phenolic resin between about 10:90 and about 75:25.
- 12. (Original) The composite as claimed in claim 8 wherein the resin binder has a weight ratio of protein hydrolysates to phenolic resin between about 25: 75 and about 75: 25.
- 13. (Original) The composite as claimed in claim 8 wherein the resin binder has a weight ratio of protein hydrolysate to phenolic resin between about 25: 75 and about 50: 50.
- 14. (Currently Amended) The composite as elaimed in claim 1 wherein the synthetic resin further comprises paraformaldehyde.
- 15. (Currently Amended) The composite as elaimed claimed in claim 14 wherein the weight ratio of the paraformaldehyde to the total of the protein hydrolysates and the synthetic resin is between about 2:48 and about 15:35 based on 50% resin solids.
- 16. (Currently Amended) The composite as claimed in claim 1 wherein the synthetic resin further comprises high methylol content phenol formaldehyde pre-polymer.
- 17. (Original) The composite as claime d in claim 16 wherein the molar ratio of formaldehyde to phenol to NaOH of the high methylol content phenol formaldehyde pre-polymer is about 2:1:0.5.
- 18. (Currently Amended) The composite as claimed in claim 16 wherein the weight

Serial No. 10/698,217

Docket No. - BAT 0033 NA/40078.251/12755CONI

ratio of the high methylol content phenol formaldehyde pre-polymer to the total of the protein hydrolysates and the synthetic resin is between about 10:90 and about 90:10.

- 19. (Currently Amended) The composite as claimed as claimed in claim 16 wherein the weight ratio of the high methylol content phenol formaldehyde pre-polymer to the total of the protein hydrolysates and the synthetic resin is between about 25: 75 and about 75: 25.
- 20. (Original) The composite as claimed in claim 1 wherein the composite further comprises a silicone, silane, or combination thereof.
- 21. (Original) The composite as claimed in clam 20 wherein the silicone, silane, or combination thereof is applied as a coating to the composite.
- 22. (Currently Amended) The composite as elaimed in claim 20 wherein the silicone, silane, or combination thereof is added to the resin binder.
- 23. (Currently Amended) The composite as <u>claimed</u> in claim 20 wherein the amount of silicone, silane, or combination thereof is between about 0.1% and about 1.0% based on the total amount of the cellulosic material.
- 24. (Previously Presented) A finished cellulosic fiber composite article prepared by the method comprising:
 - a. mixing a protein hydrolysate with a synthetic resin, wherein the synthetic resin is phenolic resin, isocyanate resin, or combinations thereof, to produce a resin binder;
 - mixing an amount of resin binder with a cellulosic material to form a
 cellulosic material/resin binder blend, wherein the amount of resin binder is
 less than 40% by weight of the cellulosic material/resin binder blend;
 - c. felting the cellulosic material/resin binder blend to form a low moisturecontent mat; and

Docket No. - BAT 0033 NA/40078.251/12755CON1

- d. molding the low moisture-content mat at an elevated temperature and pressure, producing the finished cellulosic fiber composite article.
- 25. (Original) The article as claimed in claim 24 that further comprises a laminate overlay.
- 26. (original) The composite as claimed in claim 1 wherein the synthetic resin is isocyanate resin.
- 27. (Original) The composite as claimed in claim 26 wherein the isocyanate resin is polymeric isocyanate.
- 28. (Currently Amended) The composite as elaimed claimed in claim 26 wherein the resin binder has a weight ratio of protein hydrolysates to isocyanate resin between about 10:90 and about 90:10.
- 29. (Currently Amended) The composite as elaimed in claim 26 wherein the resin binder has a weight ratio of protein hydrolysates to isocyanate resin between about 10:90 and about 75:25.
- 30. (Currently Amended) The composite as elaimed in claim 26 wherein the resin binder has a weight ratio of protein hydrolysates to isocyanate resin between about 25: 75 and about 75: 25.
- 31. (Original) The composite as claimed in claim 26 where in the resin binder has a weight ration of protein hydrolysates to isocyanate resin between about 25: 75 and about 50: 50.
- 32. (Currently Amended) The composite as elaimed claimed in claim 1 wherein the synthetic resin is a combination of phenolic resin and isocyanate resin.

Serial No. 10/698,217

Docket No. - BAT 0033 NA/40078.251/12755CON1

- 33. (Currently Amended) The composite as elaimed claimed in claim 32 wherein the weight ratio of the isocyanate resin to the total of the protein hydrolysates and the phenolic resin is between about 25: 75 and about 75: 25.
- 34. (Currently Amended) The composite as <u>claimed</u> in claim 26 wherein the amount of isocyanate resin making up the composite is about 1% to about 6% based on the total weight of the cellulosic material.
- 35. (Currently Amended) The composite as claimed claimed in claim 26 wherein the amount of isocyanate resin making up the composite is about 1% to about 3% based on the total weight of the cellulosic material.
- 36. (Currently Amended) The composite as elaimed in claim 26 wherein the amount of isocyanate resin making up the composite is about 1% to about 2% based on the total weight of the cellulosic material.